



Integrated Marketing Group

Integrated Marketing Group 138AMA

Integrated Marketing Group style 138AMA is a **specialized lightweight fiberglass fabric**, designed specifically for **industry-strength thermal protection**. This unique fabric is laminated with a high-quality vacuum metallized polyester film to create a **powerful reflective surface** that rejects up to 90% of the heat from sources up to 3000° F. With such intense heat resistance, 138AMA is the ideal fabric for thermal barriers and other thermal-protective usage.

Values

Weight	8.0 oz/sy (271.2 g/sm) +/- 10%
Thickness	0.009 inches (.2286 mm) +/- 10%
Tensile Strength	Warp: 250 lbs./inch (44.6 kg/cm) Fill: 250 lbs./inch (44.6 kg/cm)
Tear Strength	Warp: 7 lbs. (3.2 kg) Fill: 7 lbs. (3.2 kg)
Burst Strength	500 psi (35.2 kg/scm)
Flame Resistance	Char length: < 1 inch Afterglow: < 1 second Flame out: < 1 second
Temperature Resistance	-40°F - 240°F (-40°C - 115.6°C)

1740 W. Katella Ave. Suite A, Orange, CA 92867
Phone: 714-771-2401 Fax: 714-771-3925

This information is given in good faith and is believed to be accurate and correct.